

35 0 33200 10

Sonnenschein SOLAR, SOLAR BLOCK, A 600 SOLAR

Operating Instruction 33200

Stationary valve regulated lead acid batteries

Nominal data

- Nominal voltage U_N : 2.0 V x number of cells
- Nominal capacity $C_N = C_{100}$: 100h discharge (see type plate on cells/blocs and technical data in these instructions)
- Nominal discharge current $I_N = I_{100}$: $I_{100} = C_{100} / 100h$
- Final discharge voltage U_f : see technical data in these instructions
- Nominal temperature T_N : 20° C

Assembly by: _____ EXIDE Technologies order no.: _____ date: _____

Commissioned by: _____ date: _____

Security signs attached by: _____ date: _____



- Observe these Instructions and keep them located near the battery for future reference.
- Work on the battery should be carried out by qualified personnel only.



- Do not smoke.
- Do not use any naked flame or other sources of ignition. Risk of explosion and fire.



- While working on batteries wear protective eye-glasses and clothing.
- Observe the accident prevention rules as well as EN 50272-2, VDE 0105 Part 1.



- Any acid splashes on the skin or in the eyes must be flushed with plenty of clean water immediately. Then seek for medical assistance. Spillages on clothing should be rinsed out of water!



- Explosion and fire hazard, avoid short circuits.



- Electrolyte is very corrosive. In normal working conditions the contact with the electrolyte is impossible. If the cell/bloc container is damaged do not touch the exposed electrolyte because it is corrosive.



- Cells are heavy! Always use suitable handling equipment for transportation! Handle with care because cells are sensitive to mechanical shock.



- Caution! Metal parts of the battery are always alive, therefore do not place items or tools on the battery.

Non-compliance with operating instructions, repairs made with other than original parts, or repairs made without authorization (e. g. opening of valves) render the warranty void.



Disposal of Batteries

Batteries marked with the recycling symbol should be processed via a recognised recycling agency. By agreement, they may be returned to the manufacturer. Batteries must not be mixed with domestic or industrial waste.

Stationary valve regulated lead acid batteries do not require topping-up water. Pressure valves are used for sealing and can not be opened without destruction.

1. Start Up

Check all cells/blocs for mechanical damage, correct polarity and firmly seated connectors. Apply the following torques for screw connectors:

G 5	G 6	A	M 8
5 ± 1 Nm	6 ± 1 Nm	8 ± 1 Nm	20 ± 1 Nm

Rubber covers shall be fitted to both ends of the connector cables (pole covers) before installation.

Control of insulation resistance:

New batteries: > 1M Ω
Used batteries: > 100 Ω/Volt.

Connect the battery with the correct polarity to the charger (pos. pole to pos. terminal). The charger must not be switched on during this process, and the load must not be connected. Switch on charger and start charging following item 2.2.

2. Operation

For the installation and operation of stationary batteries EN 50 272-2 is mandatory.

Battery installation should be made such that temperature differences between individual cells/blocs do not exceed 3 degrees Celsius (Kelvin).

2.1 Discharge

Discharge must not be continued below the voltage recommended for the discharge time. Deeper discharges must not be carried out unless specifically agreed with the manufacturer. Recharge immediately following complete or partial discharge.

2.2 Charging

All charging must be carried out acc. to DIN 41773 (IU-characteristic).

Recommended charge voltages for cyclical application: See fig. 1 and item 2.8.

According to the charging equipment, specification and characteristics alternating currents flow through the battery superimposing onto the direct current during charge operation.

Alternating currents and the reaction from the loads may lead to an additional temperature increase of the battery, and strain the electrodes with possible damages (see 2.5), which can shorten the battery life.

2.3 Maintaining the full charge (float charge)

Devices complying with the stipulations under DIN 41773 must be used. They are to be set so that the average cell voltage is as follows (within temperature range 15 to 35° C):
SOLAR, SOLAR BLOCK: 2.30 Vpc ± 1%
A 600 SOLAR: 2.25 Vpc ± 1%

2.4 Equalizing charge

Because it is possible to exceed the permitted load voltages, appropriate measures must be taken, e.g. switch off the load. Equalizing charges are required after deep discharges and/or inadequate charges. They have to be carried out as follows: Up to 48 hours at max. 2.40 Vpc. The charge current must not exceed 35 A/100 Ah nominal capacity. The cell/bloc temperature must never exceed 45° C. If it does, stop charging or revert to float charge to allow the temperature to drop.

For system voltages ≥ 48 V every one to three months:

Method 1: IUI

I-phase = up to voltage acc. to fig.1 at 20° C
U-phase = until switching at a current of 1.2 A/100Ah to the second I-phase
I-phase = 1.2 A/100Ah for 4 hours

Method 2: IUI pulse

I-phase = up to voltage acc. to fig. 1 at 20° C
U-phase = until switching at a current of 1.2 A/100 Ah to the second I-phase (pulsed)
I-phase = charging of 2 A/100 Ah for 4-6 hours where the pulses are 15 min. 2 A/100 Ah and 15 min. 0 A/100 Ah.




Fig. 1: Charge voltage vs. temperature for solar mode. Charge modes:

- 1) With switch regulator (two-step controller): Charge on curve B (max. charge voltage) for max. 2hrs per day, then switch over to continuous charge – Curve C
- 2) Standard charge (without switching) – Curve A
- 3) Boost charge (Equalizing charge with external generator): Charge on curve B for max. 5hrs per month, then switch over to curve C.

2.5 Alternating currents

When recharging acc. to fig.1 the actual value of the alternating current is occasionally permitted to reach 10 A (RMS)/ 100 Ah nominal capacity. In a fully charged state during float charge the actual value of the alternating current must not exceed 5 A (RMS)/ 100 Ah nominal capacity.

2.6 Charging currents

The charging current should range between 10 A to 35 A / 100Ah nominal capacity (guide values).

2.7 Temperature

The recommended operation temperature range for lead acid batteries is 10° C to 30° C (best 20° C \pm 5 K). Higher temperatures will seriously reduce service life. Lower temperatures reduce the available capacity. The absolute maximum temperature is 55° C and should not exceed 45° C in service.

2.8 Temperature-related charge voltage

The temperature related adjustment has to be carried out acc. to fig. 1. An adjustment of the charge voltage must not be applied within a temperature range 15° C to 35° C.

2.9 Electrolyte

The electrolyte is diluted sulphuric acid and fixed in a gel.

3. Battery maintenance and control

Keep the battery clean and dry to avoid leakage currents. Plastic parts of the battery, especially containers, must be cleaned with pure water without additives.

At least every 6 months measure and record:

- Battery voltage
- Voltage of several blocs/cells
- Surface temperature of several blocs/cells
- Battery-room temperature

If the bloc/cell voltages differ from the average float charge voltage by values more than specified in the following table or if the surface temperature difference between blocs/cells exceeds 5 K, the service agent should be contacted.

Type	Upper value	Lower value
2 V cells	+0.2	-0.1
6 V blocs	+0.35	-0.17
12 V-blocs	+0.48	-0.24

In addition, annual measurements and recording:

- Voltage of all blocs/cells
- Surface temperature of all blocs/cells
- Battery-room temperature

Annual visual checks:

- Screw connections
- Screw connections without locking device have to be checked for tightness.
- Battery installation and arrangement
- Ventilation

4. Tests

Tests have to be carried out according to IEC 896-2, DIN 43539 part 1 and 100 (draft). Special instructions like DIN VDE 0107 and DIN VDE 0108 have to be observed.

Capacity test, for instance, acceptance test on site:

In order to make sure the battery is fully charged the following IU-charge methods must be applied: Option 1: float charge (see item 2.3), \geq 72 hours. Option 2: 2.40 Vpc, \geq 16 hours (max. 48 hours) followed by float charge (see item 2.3), \geq 8 hours. The current available to the battery must be between 10 A/100 Ah and 35 A/100Ah of the nominal capacity

5. Faults

Call the service agents immediately if faults in the battery or the charging unit are found. Recorded data as described in item 3. must be made available to the service agent. It is recommended that a service contract is taken out with your agent.

6. Storage and taking out of operation

To store or decommission cells for a longer Period of time they should be fully charged and stored in a dry and cold but frost-free room, away from direct sun light. To avoid damage the following charging methods can be chosen:

1. Maximum storage time is 17 months at \leq 20° C. Equalizing charges will be required at higher temperatures, for instance, after 8.5 months at 30° C.
2. Float charging as detailed in 2.3.

7. Transport

Cells/bloc batteries must be transported in an upright position. Batteries without any visible damage are not defined as dangerous goods under the regulations for transport of dangerous goods by road (ADR) or by railway (RID). They must be protected against short circuits, slipping, upsetting or damaging. Cells/bloc batteries may be suitable stacked and secured on pallets (ADR and RID, special provision 598). It is prohibited to staple pallets.

No dangerous traces of acid shall be found on the exteriors of the packing unit.

Cells/bloc batteries whose containers leak or are damaged must be packed and transported as class 8 dangerous goods under UN no. 2794.

8. Technical data:

Capacities at different discharge times and final discharge voltage.
All technical data refer to 20° C.

8.1 Sonnenschein SOLAR

Discharge time	1 h	5 h	10 h	20 h	100 h
Capacity	C ₁ [Ah]	C ₅ [Ah]	C ₁₀ [Ah]	C ₂₀ [Ah]	C ₁₀₀ [Ah]
S 12 / 6.6 S	2.9	4.6	5.1	5.7	6.6
S 12 / 17 G5	9.3	12.6	14.3	15	17
S 12 / 27 G5	15	22.1	23.5	24	27
S 12 / 32 G6	16.9	24.4	27	28	32
S 12 / 41 A	21	30.6	34	38	41
S 12 / 60 A	30	42.5	47.5	50	60
S 12 / 85 A	55	68.5	74	76	85
S 12 / 90 A	50.5	72	78	84	90
S 12 / 130 A	66	93.5	104.5	110	130
S 12 / 230 A	120	170	190	200	230
U _i (cell)	1.7 Vpc	1.7 Vpc	1.7 Vpc	1.75 Vpc	1.80 Vpc

8.2 Sonnenschein SOLAR BLOCK

Discharge time	1 h	5 h	10 h	20 h	100 h
Capacity	C ₁ [Ah]	C ₅ [Ah]	C ₁₀ [Ah]	C ₂₀ [Ah]	C ₁₀₀ [Ah]
SB 12 / 60	34	45	52	56	60
SB 12 / 75	48	60	66	70	75
SB 12 / 100	57	84	89	90	100
SB 12 / 130	78	101	105	116	130
SB 12 / 185	103	150	155	165	185
SB 06 / 200	104	153	162	180	200
SB 06 / 330	150	235	260	280	330
U _i (cell)	1.7 Vpc	1.7 Vpc	1.7 Vpc	1.75 Vpc	1.80 Vpc

8.3 Sonnenschein A 600 SOLAR

Discharge time	1 h	3 h	5 h	10 h	100 h
Capacity	C ₁ [Ah]	C ₃ [Ah]	C ₅ [Ah]	C ₁₀ [Ah]	C ₁₀₀ [Ah]
4 OPzV 240	108	151	175	200	240
5 OPzV 300	135	189	219	250	300
6 OPzV 360	162	227	263	300	360
5 OPzV 400	180	252	292	350	400
6 OPzV 500	225	315	365	420	500
7 OPzV 600	270	378	438	490	600
6 OPzV 720	324	454	526	600	720
8 OPzV 960	432	605	701	800	960
10 OPzV 1200	540	756	876	1000	1200
12 OPzV 1400	630	882	1022	1200	1400
12 OPzV 1700	765	1071	1241	1500	1700
16 OPzV 2300	1035	1449	1679	2000	2300
20 OPzV 2900	1305	1827	2117	2500	2900
24 OPzV 3500	1575	2205	2555	3000	3500
U _i (cell)	1.67 Vpc	1.75 Vpc	1.77 Vpc	1.80 Vpc	1.85 Vpc

EXIDE Distributionscenter Berlin
ELEKTRO.TEC GmbH
Eichborndamm 129-139
D-13403 Berlin

Tel.: +49 (0)30/4111024
Fax: +49 (0)30/4111025

www.elektrotec-berlin.de

info@elektrotec-berlin.de

State: June 2004

EXIDE
TECHNOLOGIES
INDUSTRIAL ENERGY