

Processing and handling notes of Keratherm® thermal grease (KP 12, KP 97, KP 98, KP 99) in different packagings

Keratherm® thermal compounds are silicone or mineral oil based compounds, highly filled with ceramic particles and optimized for customers' application. These products have a high thermal conductivity in the case of a low viscosity. Optimal adapting on component surfaces and compensation of smaller unevennesses are guaranteed.

Physiological notes:

Thermal greases of Kerafol® comply with valid RoHS and REACH compliance requirements.
Oils included in the thermal greases are physiologically safe.
No exposure of air is expected when using a thermal grease.
Contact to eyes and skin should be prevented by appropriate protective measures.
Using skin protection salves or other appropriate measures is recommended.
Please have a look at the references in the safety data sheets of each thermal grease.

Surface quality in application:

The component surface need to be dry and free of contaminations like oil, grease, dust, paint layers and solvent contaminations. Condensing humidity (e.g. by temperature variations) must be avoided. Depending on the condition of the component, a mechanical or chemical cleaning of the surface is eventually necessary. Please be attentive using porous heat sink or casing parts because capillary ascension in the porous surfaces may occur due to already explained migration abilities of the compounds.

Pretreatment:

Thermal greases of Kerafol® have a low viscosity and include fillers which are prone to separate to a certain level depending on storage temperature. Therefore a careful mixing process before processing is required. No binding specifications for mixing speed are present. 200-300 rpm can be used as a guideline. The mixing process have to be done smoothly to avoid air incorporation. Otherwise an evacuation process (100 mbar, ca. 5 minutes) is necessary.
Please note: Thermal greases filled in syringes and cartouches cannot be remixed.

Application:

The thickness of the thermal grease should be measured that the thermal grease fills the hollow space between the two components but not increase the distance. The most frequently error is to use too much thermal grease. The most common layout is a dot and/or a rhomb application. Therefore the viscosity and the ability of the thermal grease to level out under pressure are decisive.

The **dot application** was chosen for low viscosity greases, realizing thin layers (10 – 20 µm) and covering big areas.

The **rhomb application** was used for middle to high viscosity greases and realizing higher layer thicknesses (25 – 50 µm).

Thermal greases are of limited suitability for **screen printing** and therefore for very high layer thicknesses. In general laboratory tests need to be done to find the right layout and application.

The application of a dot and a rhomb structure with thermal grease can be done by half automated dispensing units. At high piece numbers dispensing was done on components of loaded circuit boards or on single components. After application thermal greases do not need an additional thermal treatment. Moreover fixed components should not stored over a long time line to minimize contamination or damage of the component surface and consequently a change in material performance. Applying the dispensed components to the chassis or the heat sink need to receive attention, due to the used contact pressure a levelling of the gap width take place, which have to be compensated by screws combined with springs or self-regulating clamps.

Thermal grease is not recommendable for applications with higher gap width (> 30 µm).

Processing temperature:

Keratherm® - products must be processed at temperature range from +18°C and +35°C at a relative humidity of 30 – 70%. At different temperature or humidity changes of the applying behaviour of the compounds may occur.

Storage suitability:

At least 12 month in the original packaging under frost free standard conditions: [RT // + 5°C – + 35 °C/ rel. humidity 30 – 70%]. Direct sun exposure or storage near radiators must absolutely be avoided. Opened packagings must be stored cool and protected and should be used as soon as possible.

The thermal grease KP12 show a migration of the fillers due to their low viscosity. After remixing, see pretreatment, (possible for Hobbock and small cans) the thermal grease is useable again.

Table 1: storage suitability of different bunches

bunch	room temperature + 5 °C bis + 35 °C rel.humidity 30 – 70% rolled		room temperature + 5 °C bis + 35 °C rel.humidity 30 – 70% stationary		max. usage for opened bunches	
	Hobbock	n.a.		12 month		3 month
can 0,5 l and 1,0 l	n.a.		12 month		3 month	
Thermal grease	KP12	KP97 KP98 KP99	KP12	KP97 KP98 KP99	KP12	KP97 KP98 KP99
1K-cartouche*	1 month; (3 month)**	6 month; (12 month)**	1 month; (3 month)**	3 month; (12 month)**	1 month	3 month
tube	n.a.	n.a.	1 month; (3 month)**	3 month; (12 month)**		
syringe 1 – 10 ml	n.a.	n.a.	1 month; (3 month)**	3 month; (12 month)**	1 month	3 month

*1K-cartouche = Semco-one component cartouches to 30 cc, 75 cc, 180 cc, 360 cc, 600 cc and Euro-cartouches to 310 ml (without integrated mixer)

**() = storage temperature +8 °C bis +12 °C

Transport conditions:

Clean, free of dust and moisture at min. – 40 °C to max. + 50 °C; Make sure there is no condensation on the material before processing!

General information:

Thermal greases may have a pump out effect, due to temperature variations of the components in operation mode a migration of the oil in the thermal grease can occur. Therefore the thermal grease is not edaphic and the properties in application may change (decreasing of thermal conductivity over time, etc.). If thermal greases show a separation they have to be remixed before usage.

Eschenbach, February 2021

Any specifications contained in preliminary data sheets or R&D reports are based on our present state of knowledge. All statements, technical information and recommendations contained therein are based on preliminary testing and serve as a guideline only. The final results, and all data derived therefrom, will be published after completion of all product-related testing. This shall not release the purchaser from his obligation to perform a thorough goods receipt inspection in each case. The recommendations contained herein should be verified by independent tests and trials as there are factors during processing that our outside our control, in particular when third-party raw materials have been used. Before using any these products, the purchaser must determine the suitability of the selected product for the intended use, and be aware of any associated risks and potential liability. All product specifications are subject to change in the course of technical progress or internal development. Our recommendations do not release the customer from his obligation to

Bankverbindung

Volksbank Raiffeisenbank Nordoberpfalz
IBAN: DE27 7539 0000 0001 0410 45

Kerafol Keramische Folien GmbH & Co. KG

Sitz: 92676 Eschenbach
Reg. Gericht Weiden: HRA 2846
UST-ID: DE815771797

Persönlich haftende Gesellschafterin

KERAFOL Verwaltungs-GmbH | Sitz: 92676 Eschenbach
Reg. Gericht Weiden: HRB 5098
Geschäftsführer: Franz Koppe, Isabell Koppe, Sabine Koppe

check for and, if necessary, eliminate any possible breach of third party rights. The seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. The seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be legally or contractually liable for any direct or indirect losses, damage or consequential damage, including loss of profits or revenue, arising out of the use or inability to use the product. No statement, special order or recommendations by the seller or purchaser not contained herein shall have any force or effect unless contractually and expressly confirmed by the seller and manufacturer.

Bankverbindung

Volksbank Raiffeisenbank Nordoberpfalz
IBAN: DE27 7539 0000 0001 0410 45

Kerafol Keramische Folien GmbH & Co. KG

Sitz: 92676 Eschenbach
Reg. Gericht Weiden: HRA 2846
UST-ID: DE815771797

Persönlich haftende Gesellschafterin

KERAFOL Verwaltungs-GmbH | Sitz: 92676 Eschenbach
Reg. Gericht Weiden: HRB 5098
Geschäftsführer: Franz Koppe, Isabell Koppe, Sabine Koppe