THIN WALL POLYOLEFIN TUBING

G5-3X

High shrink ratio polyolefin tubing

Applications

Operating temperature range

Designed to provide high expansion ratio, which is ideal for repairing harnesses or cables, and completely connecting and covering cable, jacket, oversize of connector, component. It's very suitable for application to irregular, awkward shapes

- Operating temperature: −55°C~135°C
- Minimum shrink temperature: 70°C
- Minimum fully recovery temperature : 100°C

Characteristics

- Shrinkage Ratio: 3:1
- Flame-retardant (colors only)
- Resistant to common fluids and solvents
- Excellent physical, chemical, and electrical properties
- Meet RoHS

Approvals / Specifications



Product Dimensions

Part Number	Nomina	ıl Size	As supplied	(mm)	After recovered	(mm)	Standard Length (M)
	mm	inch	I.D. (min)	W.T.	I.D. (max.)	W.T. (min)	
G5-3X0030	3	1/8	3.0	0.18	1.0	0.55	200
G5-3X0060	6	1/4	6.0	0.22	2.0	0.65	100
G5-3X0090	9	3/8	9.0	0.25	3.0	0.75	100
G5-3X0120	12	1/2	12.0	0.25	4.0	0.80	100
G5-3X0180	18	3/4	18.0	0.35	6.0	0.90	100
G5-3X0250	25	1	25 .0	0.45	8.0	1.20	50

roperty	Specification Requirement	Test Method	Typical Value
oncentricity	70% min.	ASTM D 2671	≥70%
ensile strength	10.4MPa min.	ASTM D 638	≥14.0MPa
longation	200% min.	ASTM D 638	≥400%
leat shock 250°C, 4hrs	No cracking, dripping or flowing	ASTM D 2671	Pass
ow temperature flexibility -55°C, 4hrs	No cracking	ASTM D 2671	Pass
ensile strength after aging (175°C/168hrs)	70% of original min.	ASTM D 638	≥90%
longation after aging(175°C/168hrs)	100% min.	ASTM D 638	≥300%
Dielectric voltage withstand	2500V, 60sec no breakdown	UL224	Pass
ielectric strength	19.7KV/mm min.	ASTM D 2671	25KV/mm
olume resistivity	10 ¹⁴ Ω • cm min.	ASTM D 876	≥10 ¹⁴ Ω · cm
Corrosion	No corrosion	ASTM D 2671	Pass
lammability	VW-1	UL2244	Pass



Color: black ` white ` red ` blue ` yellow ` green ` clear, other colors on request. Special size, cutting pieces are available on request.









