

Distributed by Conrad Electronic SE • Klaus-Conrad-Str. 1 • D-92240 Hirschau

### Datasheet

Item no. 1567327 1567328 1567329 1570283

V2\_02222022\_01\_en

#### Powered by CO-APEX

# Medium Wall Polyolefin Tubing (ATM series)

Part Number	Model no.	As supplied (mm)	After recovered (mm)		Chainly an ortic	Steads and In math (Masters)	
		I.D. (min.)	I.D. (max.)	W.T. (min)	Shrinkage ratio	Standard length (Meter)	
ATM medium wall tubing with hot melt adhesive							
1567327	AT M008	8	2	1.7	4:1	1.22	
1567328	AT M012	12	3	1.8	4:1	1.22	
1567329	AT M028	28	6	2.5	4:1	1.22	
1570283	AT M033	33	8	2.5	4:1	1.22	

Property	Test Method	Typical Value
Operating temperature	IEC 216	-55°C ~ +110°C
Tensile strength	ASTM D 2671	≧14 MPa
Elongation at break	ASTM D 2671	≧400%
Density	ASTM D 792	1.05g/cm <sup>3</sup>
Longitudinal shrinkage	UL 224	0~10%
Eccentricity	ASTM D 2671	<30%
Elongation at break after aging	150°C, 168hrs	≧300%
Dielectric strength	IEC 243	≧20KV/mm
Volume resistance	IEC 93	≧10 <sup>14</sup> Ω•cm
Copper stability	ASTM D 2671	Pass
Resistance to stress cracking (50°C)	ASTM D 1693	No cracking
Water absorption	ISO 62	< 0.15%

This is a publication by Conrad Electronic SE, Klaus-Conrad-Str. 1, D-92240 Hirschau (www.conrad.com).

All rights including translation reserved. Reproduction by any method, e.g. photocopy, microfilming, or the capture in electronic data processing systems require the prior written approval by the editor. Reprinting, also in part, is prohibited. This publication represents the technical status at the time of printing.

© Copyright 2017 by Conrad Electronic SE.



Distributed by Conrad Electronic SE • Klaus-Conrad-Str. 1 • D-92240 Hirschau

## Datasheet

Item no. 1567327 1567328 1567329 1570283

V2\_02222022\_01\_en

2

### Powered by G.APEX

Thermoplastic Adhesive				
Property	Test Method	Typical Value		
Water absorption	ISO 62	<0.2%		
Softening point	ASTM D E28	85°C		
Peel strength (PE)	DIN 30672	4N/cm		
Copper stability	ASTM D 2671	Non-corrosive		
Resistance to fungus and decay	ISO 846	Pass		

Applications:

High shrink ratio and hot melt adhesive, which provide excellent properties of insulation and protection to cable joints and terminations. And high abrasion and corrosion resistance for applying in communication cable and pipe.

Characteristics: Shrinkable Ratio: 4:1 Easily fit over irregular shape and large connectors Resistant to UV and waterproof Excellent electrical insulation

Operating temperature range: Operating temperature: -55°C to 110°C Minimum shrink temperature: 80°C Minimum fully recovery temperature: 120°C

Material: Tubing: Polyolefin Hot melt adhesive: EVA

Color: Black



This is a publication by Conrad Electronic SE, Klaus-Conrad-Str. 1, D-92240 Hirschau (www.conrad.com).

All rights including translation reserved. Reproduction by any method, e.g. photocopy, microfilming, or the capture in electronic data processing systems require the prior written approval by the editor. Reprinting, also in part, is prohibited. This publication represents the technical status at the time of printing.