

Data Sheet

ASM – Heavy Wall Heat Shrink Tubing



Applications:

It is made of polyolefin and hot melt adhesive.

ASM has a thicker wall thickness for better outer protection.

With excellent abrasion and corrosion resistance, it is suitable for the insulation protection of cables and terminals and is widely used in communications, power cables and chemical pipelines.

Operating temperature range:

Continuous operating temperature: -55°C~110°C

Min. shrink temperature: 80°C

Full recovery temperature: Above 120°C

Shrinkage: 3:1

BN	As supplied (mm)	After recovered (mm)		Standard Length (Meter)
	I.D. (min)	I.D. (max)	Wall thickness (min.)	
1567334	9	3	1.8	1.22
1567335	13	4	2.5	1.22
1567336	22	6	2.7	1.22
1572307	33	8	3.2	1.22
1570284	40	12	4.1	1.22
1567337	45	12	4.1	1.22