Heat Shrinkable Tubing 2:1 - Flame retardant TR27

TR27 is used in applications where toxic emissions evolved in a fire must be minimised, e.g. heavily populated buildings or safety sensitive areas like tunnels, hospitals, schools, theatres, mass transit vehicles and computer centres.

Features and Benefits

- Thin walled, flexible polyolefin tubing
- Optional available with adhesive or as thick walled version (SR27)
- Halogen free and excellent flame-retardant properties
- Meets various industrial standards

MATERIAL	Polyolefin, cross-linked (PO-X)				
Shrink Ratio	2:1				
Operating Temperature	-40 °C to +105 °C				
Minimum Shrink Temperature	+115 °C				
Longitudinal change after shrinkage	+5 %/-10 % max.				
Dielectric Strength	15 kV/mm according to IEC 60684 P2				
Flammability	Limited Fire Hazard, Halogen free, Low generation of toxic gases and corrosive acid, Low smoke generation				
Specifications	DEF STAN 59-97 Type 8, EN 45545: 2013, LUL Engineering Standard E1042:A6				





TR27 is ideal for safety sensitive areas.



TR27 is mainly used in the railway industry.





Heat Shrinkable Tubing 2:1

	Detailed Information about					
∥₽I	Detailed information about					
	Detailed Information about Heatquns please refer to page 529.					

TYPE	Supplied	Size	Recov.	Wall	Reel	C-1	Audiala Na
ITPE	Ø D min.	(imperial)	Ø d max.	(WT)	Length	Colour	Article-No.
TR27-3.2/1.6	3.2	1/8 "	1.6	0.51	150 m	Black (BK)	315-50320
TR27-4.8/2.4	4.8	3/16 "	2.4	0.51	60 m	Black (BK)	315-50480
TR27-6.4/3.2	6.4	1/4 "	3.2	0.64	60 m	Black (BK)	315-50640
TR27-9.5/4.8	9.5	3/8 "	4.8	0.64	60 m	Black (BK)	315-50950
TR27-12.7/6.4	12.7	1/2 "	6.4	0.64	60 m	Black (BK)	315-51270
TR27-19.1/9.5	19.1	3/4 "	9.5	0.76	60 m	Black (BK)	315-51900
TR27-25.4/12.7	25.4	1 "	12.7	0.89	60 m	Black (BK)	315-52540
TR27-38.1/19.1	38.1	1-1/2 "	19.1	1.02	60 m	Black (BK)	315-53810
TR27-50.8/25.4	50.8	2 "	25.4	1.14	60 m	Black (BK)	315-55100

All dimensions in mm. Subject to technical changes. Minimum Order Quantity (MOQ) may differ from package content.



For product specific approvals and specifications please refer to the Appendix.