

PRODUCT

Silica Gel Desiccant



Silica gel is a transparent spheroidal particle. The main component is SiO₂. Because of the large surface area, silica gel has a high moisture absorption rate. Silica gel can be reactivated without affecting its moisture absorption capacity. It is therefore very economical.

TECHNICAL SPECIFICATION

ITEM/CONDITION		STANDARD
Moisture absorption capacity (T=25 ±2 °C)	RH=20±2%	≥9.5%
	RH=50±2%	≥22.0%
	RH=90±2%	≥33.0%
IPH		4~8
Specific Resistance		≥3000Ω.cm
Granularity Percent of Pass%		≥90%
Bulk Density g/L		≥750

Silica gel desiccant must always be kept in airtight containers to avoid moisture absorption.

To request a quotation or for more information, please call **+44 (0)1473 836200**
email info@antistat.co.uk or visit www.antistat.co.uk

IMPORTANT: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © 2021 Antistat.

PACKAGING MATERIAL

ITEM		NO	STANDARD
Quantitative (g/m ²)		A	77±5
Thickness (um)		B	115±10
WVTR g/m ² 24hr		C	≥2000
Seal strength N/15mm		D	≥5
Breaking capacity	MD (N/15MM)	E	190-170
	CD (N/15MM)	F	95-70
Elongation at break	MD (%)	G	18
	CD (%)	H	18
Seal Temperature °C		I	110-160
Sealing time (S)		J	0.7-2
Sealing pressure (Mpa)		K	0.4-0.6
Composition		P	Non woven + breathable film

To request a quotation or for more information, please call **+44 (0)1473 836200**
 email info@antistat.co.uk or visit www.antistat.co.uk

IMPORTANT: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. © 2021 Antistat.