

86 / 25 KERATHERM®




PRELIMINARY DATA SHEET

Benefits

- high thermal conductivity
- high electrical isolation
- easy handling
- optional available with adhesive coating

Properties	Unit	86 / 25
Colour		mint
Thermal Properties*		
Thermal resistance R_{th}	K/W	0.225
Thermal conductivity λ	W/mK	2.5
Electrical Properties*		
Dielectric breakdown voltage $U_{d, AC}$	kV	3.5
Volume resistivity	Ωm	$1,5 \times 10^{11}$
Dielectric loss factor $\tan \delta$		8×10^{-3}
Dielectric constant ϵ_r		1,9
Mechanical Properties		
Hardness	Shore A	60 - 75
Tensile strength	N/mm ²	tbd
Elongation	%	tbd
Physical Properties		
Application temperature	°C	-60 to +200
Density	g/cm ³	2.37
Possible thickness	mm	0.225

* Measured @ thickness 0.225 mm



✓ Optional available with
onside adhesive coating **86/25 K**



Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. KERAFOLE® is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. All specifications are subject to change without notice. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded. In case KERAFOLE® would be nevertheless held liable, on whatever legal ground, KERAFOLE®'s liability will in no event exceed the amount of the concerned delivery. All KERAFOLE® products are sold pursuant to the KERAFOLE®'s Terms and Conditions of sale and delivery in effect from time to time, a copy of which will be furnished upon request.

05-2024